



Delta Polymers, Inc.

Tel: (800) 966-5142
(631) 254-6240
Fax: (631) 595-2537
www.deltapolymers.com
E-mail: info@deltapolymers.com

MANUFACTURERS OF HIGH PERFORMANCE
EPOXY & POLYURETHANE FLOORING SYSTEMS

PolySeal - 3300

Epoxy penetrating sealer

DESCRIPTION:

PolySeal-3300 is a two component epoxy penetrating sealer for concrete and masonry surfaces. It has the ability to penetrate deeply and increase the strength and chemical resistance of the treated area. Its high solid contents of 75% and a very low viscosity makes it a unique product which meets V.O.C requirements of the E.P.A.

USES:

- Bridge Decks · Food Service Areas
- Concrete Highways · Aircraft Hangers
- Garage Floors · Machine Shop Floors
- Parking Garage Decks · For increase in strength and chemical resistance where necessary.

PROPERTIES:

Mixing Ratio Base to Hardener by volume 2:1

Pot Life 75°F, Hrs. 1

Solids % 75

Mixed Viscosity at 75°F CPS 100

Tensile Strength PSI 4,000-5,000

(Evaporate all the solvents and make samples.)

Tensile Elongation % 1 to 5

SURFACE PREPARATION:

Surface must be clean, dry and free from any dirt, grease, oils, previous coatings or any other contaminants which will interfere with penetration and bond.

MIXING:

Combine one part of base to one part hardener by volume. Mix thoroughly and use immediately.

APPLICATION:

Apply with roller, squeegee, brush or spray. For best results allow at least 10 to 12 hours between coats.

COVERAGE:

Penetration will vary with the type, porosity and surface condition. 120-150 square feet per gallon per coat.

Non-Warranty

This product is made under strict quality control procedures of Delta Polymers, Inc. No guarantee is given or implied. We assume no responsibility for coverage, performance or injuries resulting from use. Liability if any is limited to replacement of products which are defective in manufacture. No other warranty or guarantee of any kind is made by the seller, express or implied, statutory by operation or law or otherwise, including merchantability and fitness for a particular purpose.

Caution

Avoid contact with eyes and prolonged contact with skin. In case of eye contact, flush with plenty of water for at least 15 minutes and seek medical attention. For skin wash with soap and water. keep away from children. For details see product data sheet and MSDS.